

**EN** - For pricing and availability in your local country please visit one of the below links:

**DE** - Informationen zu Preisen und Verfügbarkeit in Ihrem Land erhalten Sie über die unten aufgeführten Links:

**FR** - Pour connaître les tarifs et la disponibilité dans votre pays, cliquez sur l'un des liens suivants:

[FM699](#)

**EN**

This Datasheet is presented by  
the manufacturer

**DE**

Dieses Datenblatt wird vom  
Hersteller bereitgestellt

**FR**

Cette fiche technique est  
présentée par le fabricant

# Datasheet

## Magnetic Tape Strip



### At A Glance

- Flexible magnetic material
- Easily cut to length
- Adhesive backed for quick fixing
- Multiple poles on one face
- Pre-cut to 100mm lengths

Our Magnetic Tape Strip is pre-cut to 100mm lengths for use in creating magnetic displays / magnetic signage. The Magnetic Tape Strip is flexible and very easy to cut to length but is already pre-cut to 100mm (3.93inch) lengths for convenience. It is a Strontium Ferrite magnetic material combined with a thermo-plastic binder.

It is magnetised multiple poles on one side only; the other side has the adhesive layer and release liner.

The adhesive layer is 0.04-0.05mm thick (rough guide) - it is not included in the thickness values (so, without the release liner, a 0.75mm thick tape would actually measure about 0.80mm thick). The adhesive layer is a standard acrylic adhesive covered with a protective quick release liner. Once you have cut the Magnetic Tape to your required length (using scissors or a craft knife) simply peel away the protective adhesive liner and firmly press the adhesive layer onto the part you want it to adhere to. The adhesive is a pressure adhesive - it needs a firm press to get the adhesive to work properly. The standard acrylic adhesive is ideal for applying to cardboard and paper.

Magnetic Performance is stated as a pull force per unit of surface area and is dependent on the magnetic material thickness. The higher rated materials work better through gaps such as sheet(s) of paper - 0.75mm is rated at 44g/cm<sup>2</sup> (0.625lb/in<sup>2</sup>). Above 60 degrees C the magnetic pattern will soften and weaken; below -20 degrees C the magnetic material risks starting to demagnetise. It is usually used against ferrous surfaces such as steel tape, fridge doors, etc. It can also be used against another Magnetic tape but bear in mind the polarities may not line up in attraction perfectly. The FM699/F is cut/slit from a larger magnetic sheet into 12.7mm widths that are 100mm long - the way it is cut means that it is magnetised multiple pole along its length so it may not overlap perfectly against itself lengthways and will not align well against 'A', 'B' or 'Self-Mating' magnetised pattern tapes. For note, the more surface area used, the more the magnetic tape will hold onto the surface. For maximum performance, you need direct contact - as soon as you put anything in the way, the pull force starts to reduce.

### Benefits

- Flexible magnetic material
- Easily cut to length but is Pre-Cut to 100mm (3.93inch) lengths
- Acrylic adhesive backing with quick release liner - press in place to bond
- Up to 60°C (140°F) maximum recommended operating temperature
- Magnetised as multiple poles on one side for improved direct contact hold

### Materials

Magnetic Material	Strontium Ferrite (isotropic) in thermo-plastic binder
Other Parts	Acrylic adhesive, adhesive liner

### Performance

Magnetic Performance	Up to 44g/cm <sup>2</sup> (0.625lb/in <sup>2</sup> ) pull force rating
Magnet Type	Isotropic Strontium Ferrite in a binder

### Suitability

Suitable Products	Ferrous materials (e.g. mild steel, fridge doors, etc)
Suitable Location	Packaging, Point of Sale, Arts & Craft, Retail, etc

### Maintenance

- There is no specific maintenance or cleaning requirements for this product
- Keep part warmer than -40°C (-40°F), ideally above -20°C (-4°F)
- Keep part cooler than +60°C (+140°F)

### Alternatives


- Magnetic Tape / Premium acrylic Magnetic Tape (longer length reels)
- Foam-backed acrylic Magnetic Tape (better for adhesion to uneven surfaces)
- Magnetic Extrusion (more pull); Magnetic Sheet (wider plain, vinyl, adhesive)

### Display Range



# Datasheet

## Magnetic Tape Strip



Product Number	Dimensions			Weight (kg)	Backing Material	Multiple Poles Layout	Specific Polarity Type**	Pull Force* g/cm <sup>2</sup>	Units per Pack
	Width (mm)	Thickness (mm)	Length (m)						
FM699/F	12.7	0.75	0.1	0.044	Acrylic adhesive backed	Across width	N/A	44	10

\* The pull force is based on the Magnetic Tape pulling in direct contact (no air gap) against a thick mild steel surface.

\*\* The FM699/F is magnetised multiple pole along the length - it only attracts to itself or a ferrous surface.

Magnetic Tape is magnetised multiple parallel pole across its surface. 'Self-Mating' materials can magnetically overlay in attraction to each other in near perfect alignment. 'A' material will magnetically overlap near perfectly against 'B' material. It is possible to overlap 'A' against 'A' or 'B' against 'B' but there may be a slight offset in overlap (sometimes reduced if you turn the ends of one of the tapes around (offset due to magnetic poles needing to align in an attractive layout of North pulling a South on the other part)). Products listed above as N/A are actually cut (slit) from much wider rolls so they have the same magnetic pole pattern type as the 'A' and 'B' but the start position of a pole relative to the edge of the width may vary, so it will attract to itself or the 'A' and/or 'B' types but alignment position may vary between rolls.

If any Magnetic Tape is put against a mild Steel Tape (or any other ferrous surface e.g. fridge door, metal filing cabinet), it will attract and magnetically hold in place. It can then be slid into optimum place as needed.

For further assistance, please contact [sales@eclipsemagnetics.com](mailto:sales@eclipsemagnetics.com)

Although we have made every attempt to provide accurate information, we do reserve the right to change any of the information in this document without notice.

We cannot accept any responsibility or liability for any errors or problems caused by using any of the information provided.

### Conversions Guide:-

28g/cm<sup>2</sup> ≈ 0.398lb/in<sup>2</sup>

44g/cm<sup>2</sup> ≈ 0.625lb/in<sup>2</sup>

55g/cm<sup>2</sup> ≈ 0.782lb/in<sup>2</sup>

(the above conversion values are rounded down)



**EN** - For pricing and availability in your local country please visit one of the below links:

**DE** - Informationen zu Preisen und Verfügbarkeit in Ihrem Land erhalten Sie über die unten aufgeführten Links:

**FR** - Pour connaître les tarifs et la disponibilité dans votre pays, cliquez sur l'un des liens suivants:

[FM699](#)

**EN**

This Datasheet is presented by  
the manufacturer

**DE**

Dieses Datenblatt wird vom  
Hersteller bereitgestellt

**FR**

Cette fiche technique est  
présentée par le fabricant